

Process for the automatic application of a protective lacquer onto optical glass blanks, useful for lenses, comprises heating the blanks to a specified low temperature and applying the protective lacquer.

Patent number: DE10017363
Publication date: 2001-10-18
Inventor: GEBAUER MANFRED (DE); HUEFFTLEIN KARLHEINZ (DE)
Applicant: RMH POLYMERS GMBH & CO KG (DE)
Classification:
- **International:** C03C17/00; B05D1/26; B05D1/02
- **European:** C03C17/32, C03C17/00B
Application number: DE20001017363 20000407
Priority number(s): DE20001017363 20000407

Abstract of DE10017363

A process for the automatic application of a protective lacquer onto optical glass blanks comprises laying the blanks on to the sliding plate of a linear unit; passing the blanks at a constant speed via a vacuum distributor to a heat source to heat the blanks to 35-60 deg C, passing the blanks under an application system for the protective lacquer and heating the coated blanks in air. A process for the automatic application of a protective lacquer onto optical glass blanks comprises decentrally gripping optical glass blanks supplied to a job tray by means of a spin gripper and laying the blanks on to the sliding plate of a linear unit; passing the blanks at a constant speed via a vacuum distributor to a heat source to heat the blanks to 35-60 deg C; passing the sliding plate at the same speed under an application system for the protective lacquer and optionally situating an application vat for recovery of the protective lacquer; passing the sliding plate through a channel having a heat source and counter air stream and again laying the optical glass blanks onto a job tray.

Data supplied from the **esp@cenet** database - Worldwide